

Technical Data

WP EPOXY FLOOR PRIMER CLEAR EFP-085

DESCRIPTION

A two-pack polyamide cured epoxy to prepare floor repair mortars undercoat. Self-leveling, good abrasion, impact resistance, quick drying, and good resistance to wide spectrum of chemicals

USES

As excellent adhesion agent to concrete, masonry and other building material.

SPECIFICATION

Color / Texture	Clear / Semi gloss
Volume solids	83%
Specific Gravity	1.4 (after mixing)
Mixing Ratio	2 parts BASE mixed with 1 part HARDENER
Pot Life (30°C)	1 hour
Flash Point	24°C
Theoretical Coverage	4.3 m ² /l at 200 microns
Surface Dry (30°C)	2 hours
Hard Dry (30°C)	12 hours
Dry to Recoat	12 hours
Fully Cured	7 days
Thinner / Cleaner	WP Epoxy Thinner W-004
Standard Packing	5 litres set and 20 litres set

METHOD OF APPLICATION

Trowel	Dilution	0 - 5% Thinner W-004
--------	----------	----------------------

SURFACE PREPARATION

Ensure primed surface are clean, dry and free from rust, salt, oil, grease and other contaminants.

MIXING

Stir the BASE paint until mixed to a uniform consistency. While stirring, add the HARDENER slowly to the BASE, then stir the mixture thoroughly.

STORAGE

Store in cool and dry space provided with adequate ventilation.

SAFETY PRECAUTION

This product is inflammable, keep away from sparks or open flames. Avoid skin contact. Spray under well ventilated conditions. Do not breathe or inhale mist of paint.