

Technical Data

WP EPOXY FLOOR PRIMER EFP-065

DESCRIPTION

A two-pack Polyamide cured epoxy floor coating. Resist fumes and spillage of solvent, alkalis, mid acid and salt.

USES

As a high build semi-gloss finish for the protection of concrete.

SPECIFICATION

Color / Texture	Grey, Cream, Green / Semi gloss
Volume solids	65%
Specific Gravity	1.2 (after mixing)
Mixing Ratio	4 parts BASE mixed with 1 part HARDENER
Pot Life (30°C)	4 hours
Flash Point	24°C
Theoretical Coverage	6.5 m ² /l at 100 microns
Surface Dry (30°C)	2 hours
Hard Dry (30°C)	12 hours
Dry to Recoat	12 hours
Fully Cured	7 days
Thinner / Cleaner	WP Epoxy Thinner W-004
Standard Packing	20 litres set

METHOD OF APPLICATION

Airless Spray	Nozzle tip	0.38 - 0.53 mm
	Pressure	140 - 170 kg/cm ² 2500 psi
	Dilution	0 - 5% Thinner W-004
Brush or Roller	Dilution	0 - 5% Thinner W-004

SURFACE PREPARATION

Ensure primed surface are clean, dry and free from rust, salt, oil, grease and other contaminants.

MIXING

Stir the BASE paint until mixed to a uniform consistency. While stirring, add the HARDENER slowly to the BASE, then stir the mixture thoroughly.

STORAGE

Store in cool and dry space provided with adequate ventilation.

SAFETY PRECAUTION

This product is inflammable, keep away from sparks or open flames. Avoid skin contact. Spray under well ventilated conditions. Do not breathe or inhale mist of paint.