

Technical Data

WP ZINC CHROMATE PRIMER C-11

DESCRIPTION

A relatively fast drying rust preventive primer based on alkyd resins with Zinc Chromate pigments.

USES

Prevention of corrosion for steel, light alloys and galvanized surfaces. Recommended for use on interior top sides and super structures.

SPECIFICATION

Color / Texture	Grey, Green / Matte
Volume solids	55%
Specific Gravity	1.35
Film Thickness - Wet	75 microns
Film Thickness - Dry	40 microns
Theoretical Coverage	6.5 m ² /l at 80 microns
Surface Dry (30°C)	30 minutes
Hard Dry (30°C)	6 hours
Dry to Recoat	6 hours
Flash Point	32°C
Thinner / Cleaner	WP Standard Thinner W-003
Standard Packing	5 litres and 20 litres

METHOD OF APPLICATION

Airless Spray	Nozzle tip	0.38 - 0.53 mm
	Pressure	140 - 170 kg/cm ² 2100 psi
	Dilution	0 - 5% Thinner W-003
Brush or Roller	Dilution	0 - 5% Thinner W-003

SURFACE PREPARATION

The surface must be clean and dry, free from dust, oil and other contaminants.

MIXING

Stir material thoroughly for 2 - 3 minutes before application. If necessary use WP Standard Thinner W-003.

STORAGE

Store in cool and dry condition.

SAFETY PRECAUTION

This product is inflammable, keep away from sparks or open flames. Avoid skin contact. Spray under well ventilated conditions. Do not breathe or inhale mist of paint.